

SKY-SCAPES®

UL Information

UL723	Surface Burning Characteristics-Flame Spread Index	164
UL723	Surface Burning Characteristics-Smoke Spread Index	614

The UL723 test is equivalent to ASTM E-84. The test results for this test is:

ASTM E-84	Flame Spread Index (dimensionless)	135 @ 0.125" sht.
		115 @ 0.236" sht.
		110 @ 0.375" sht.

ASTM E-84	Smoke Developed Index (dimensionless)	>450 @ 0.125" sht.
		550 @ 0.236" sht.
		605 @ 0.375" sht.

These tests are also equivalent to:	Uniform Building Code (UBC) 42-1
	ANSI/FPA 255
	UBC 8-1

**An outside company, Lumican, a distributor of acrylic sheet, provided this UL723 information. The test was conducted in 1995.*